

12

Abstract

5 A zirconium-based alloy, suitable for use in a corrosive environment, where it is subjected to increased radiation and comprises 0.5-1.6 percentage by weight Nb and 0.3-0.6 percentage by weight Fe. The alloy is characterised in that it comprises 0.5-0.85 percentage by weight Sn.

10